

Level 0
0 - <10 min

Level 1
10 - 30 min

Level 2
30 - 60 min

Level 3
60 - 120 min

Level 4
120 - 240 min

Level 5
240 - 480 min

Level 6
< 480 min

ecoSHIELD* Eco Nitrile PF 250



0120

EN374:2003



LEVEL 3

EN374:2003



- Category III PPE glove (PPE Directive 89/686/EEC)
- Complex Design - For mortal and irreversible risks
- Powder-free green/white nitrile glove
- twinSHIELD* double-walled protection
- Ambidextrous
- 250 mm / 0.10 mm (XL/10: 260 mm) (EN 420:2003 + A1:2009)
- AQL 0.65 (EN 374-2:2014 Level 3)
- Viral penetration test (ISO 16604:2004 Procedure B & ASTM F1671-97b)
- Waterproof and for low chemical protection
- Tested for chemical permeation (EN 16523-1:2015 supersedes EN 374-3:2003)
- Type I hypersensitivity eliminated - Type IV hypersensitivity reduced

64742-49-0
Petroleum benzene 80-100°C

LEVEL 6
480 min

66-81-9
Cycloheximide

LEVEL 6
480 min

Mixed Solution
Hydranal® -Composite 2

LEVEL 6
480 min

Mixed Solution
Mucocit®-T branded mixture

LEVEL 6
480 min

10127-02-3
Acridine orange

LEVEL 6
480 min

77-86-1
Tris (hydroxymethyl) aminomethane Sat. solution

LEVEL 6
480 min

127-09-3
Sodium acetate Sat. solution

LEVEL 6
480 min

7664-93-9 Sulphuric acid 50%	LEVEL 6 480 min
108-95-2 Phenol 0.1% solution	LEVEL 6 480 min
75-59-2 Tetramethylammonium hydroxide 2.5%	LEVEL 6 480 min
7664-93-9 Sulphuric Acid 10%	LEVEL 6 480 min
7681-52-9 Sodium Hypochlorite 13%	LEVEL 6 480 min
1310-58-3 Potassium Hydroxyde 40%	LEVEL 6 480 min
1310-73-2 Sodium Hydroxide, 50%	LEVEL 6 480 min
1310-73-2 Sodium Hydroxide 40%	LEVEL 6 480 min DR 10%
7664-38-2 Phosphoric Acid, 30%	LEVEL 6 480 min
7722-84-1 Hydrogen Peroxide 30%	LEVEL 6 480 min
1239-45-8 Ethidium bromide 5%	LEVEL 6 480 min
7803-57-8 Hydrazine monohydrate 98%	LEVEL 4 150 min
7647-01-0 Hydrochloric Acid 37%	LEVEL 3 98 min
50-00-0 Formaldehyde 37%	LEVEL 3 87 min DR 25%

67-56-1 Methanol, 20%	LEVEL 3 65 min
124-18-5 n-Decane	LEVEL 2 58 min
67-63-0 Isopropanol 70%	LEVEL 2 58 min
108-87-2 Methylcyclohexane 99,9%	LEVEL 2 55 min
Mixed Solution Bacillol 30 Foam	LEVEL 2 48 min
110-82-7 Cyclohexane	LEVEL 6 480 min
79-06-1 Acrylamide 40%	LEVEL 6 480 min
142-82-5 n-Heptane 99%	LEVEL 2 41 min DR 48%
78-83-1 Isobutanol 99%	LEVEL 2 39 min
67-63-0 Isopropanol 100%	LEVEL 2 33 min
64-17-5 Ethanol 70%	LEVEL 2 31 min
598-75-4 Secondary isoamyl alcohol 98%	LEVEL 2 30 min
110-54-3 n-Hexane 95%	LEVEL 1 28 min
71-36-3 Butanol 99,4%	LEVEL 1 25 min

Mixed Solution Bacillol AF	LEVEL 1 22 min
108-95-2 Phenol 50%	LEVEL 1 15 min
75-12-7 Formamide 99%	LEVEL 1 11 min
62-53-3 Aniline 99,9%	LEVEL 1 10 min
97-88-1 Butyl methacrylate 99,9%	LEVEL 1 10 min
67-68-5 Dimethyl Sulfoxide 99% (DMSO)	LEVEL 1 10 min
64-17-5 Ethanol 99.8%	LEVEL 0 9 min
7664-39-3 Hydrofluoric Acid 40%	LEVEL 0 8 min
64-19-7 Acetic Acid 100%	LEVEL 0 4 min
7697-37-2 Nitric Acid 70%	LEVEL 0 4 min
64-18-6 Formic acid 97.8%	LEVEL 0 3 min
1330-20-7 Xylene 98,5%	LEVEL 0 2 min
1336-21-6 Ammonium Hydroxide 25%	LEVEL 1 16 min
60-24-2 2-Mercaptoethanol 99%	LEVEL 0 1 min

68-12-2 Dimethyl Formamide 99%	LEVEL 0 1 min
584-84-9 Toluene diisocyanate 95%	LEVEL 0 0 min
75-56-9 Propylene oxide 99%	LEVEL 0 0 min
7664-93-9 Sulphuric acid 95%-98%	LEVEL 0 0 min
60-29-7 Diethyl ether 99%	LEVEL 0 0 min
75-15-0 Carbon Disulfide 99,9%	LEVEL 0 0 min
76-05-1 Trifluoroacetic acid 99%	LEVEL 0 0 min
67-64-1 Acetone 99,8%	LEVEL 0 0 min
109-99-9 Tetrahydrofuran 99.9%	LEVEL 0 0 min
100-42-5 Styrene 99.9%	LEVEL 0 0 min
110-86-1 Pyridine	LEVEL 0 0 min
75-09-2 Dichloromethane 99%	LEVEL 0 0 min
67-56-1 Methanol 99,9%	LEVEL 0 0 min
7664-39-3 Hydrofluoric Acid 48%	LEVEL 0 0 min

64-18-6
Formic acid 98,5%
LEVEL 0
0 min

141-78-6
Ethyl Acetate 99.8%
LEVEL 0
0 min

109-89-7
Diethylamine 99,5%
LEVEL 0
0 min

67-66-3
Chloroform 99,8%
LEVEL 0
0 min

107-13-1
Acrylonitrile 99%
LEVEL 0
0 min

75-05-8
Acetonitrile 99,9%
LEVEL 0
0 min

