

Level 0
0 - <10 min

Level 1
10 - 30 min

Level 2
30 - 60 min

Level 3
60 - 120 min

Level 4
120 - 240 min

Level 5
240 - 480 min

Level 6
< 480 min

SHIELDskin XTREME* Sterile ORANGE NITRILE* 300 DI




0120

EN374:2003



LEVEL 3

EN374:2003



- Category III PPE glove (PPE Directive 89/686/EEC)
- Complex Design - For mortal & irreversible risks
- Powder-free orange nitrile/polychloroprene glove
- Hand-specific
- 300 mm / 0.12 mm (EN 420:2003 + A1:2009)
- AQL 0.65 (EN 374-2:2014 Level 3)
- Viral penetration test (ISO 16604:2004 Procedure B & ASTM F1671-97b)
- Waterproof and for low chemical protection
- Tested for chemical permeation (EN 16523-1:2015 supersedes EN 374-3:2003)
- Typical particle levels: less than 2500 per cm² more or equal 0.5µm
- Type I hypersensitivity eliminated - Type IV hypersensitivity reduced

Mixed Solution
Perform sterile PAA ready to use

LEVEL 6
480 min

Mixed Solution
Perform sterile concentrate PAA 3%

LEVEL 6
480 min

Mixed Solution
Perform sterile concentrate Oxy 2%

LEVEL 6
480 min

Mixed Solution
Mucocit®-T branded mixture

LEVEL 6
480 min

50-01-1
Guanidine Hydrochloride

LEVEL 6
480 min

10127-02-3
Acridine orange

LEVEL 6
480 min

77-86-1
Tris (hydroxymethyl) aminomethane Sat. solution

LEVEL 6
480 min

127-09-3 Sodium acetate Sat. solution	LEVEL 6 480 min
7664-93-9 Sulphuric acid 50%	LEVEL 6 480 min
76-03-9 Trichloroacetic acid 10%	LEVEL 6 480 min
7803-57-8 Hydrazine monohydrate 80%	LEVEL 6 480 min
7664-93-9 Sulphuric Acid 10%	LEVEL 6 480 min
7681-52-9 Sodium Hypochlorite 13%	LEVEL 6 480 min
1310-58-3 Potassium Hydroxyde 40%	LEVEL 6 480 min
7722-84-1 Hydrogen Peroxide 12%	LEVEL 6 480 min
111-30-8 Gluteraldehyde 2.5%	LEVEL 6 480 min
77-92-9 Citric acid 30%	LEVEL 6 480 min
1310-73-2 Sodium Hydroxide, 50%	LEVEL 6 480 min
1310-73-2 Sodium Hydroxide 40%	LEVEL 6 480 min
7664-38-2 Phosphoric acid, 85%	LEVEL 6 480 min
7664-38-2 Phosphoric Acid, 30%	LEVEL 6 480 min

540-84-1 Iso-Octane 99%	LEVEL 6 480 min
7722-84-1 Hydrogen Peroxide 30%	LEVEL 6 480 min DR 22%
111-30-8 Glutaraldehyde 25%	LEVEL 6 480 min
50-00-0 Formaldehyde 37%	LEVEL 6 480 min
50-00-0 Formaldehyde 10%	LEVEL 6 480 min
1239-45-8 Ethidium bromide 5%	LEVEL 6 480 min
7803-57-8 Hydrazine monohydrate 98%	LEVEL 4 180 min
54-11-5 Nicotine 98%	LEVEL 4 151 min
7647-01-0 Hydrochloric Acid 37%	LEVEL 3 116 min
Mixed Solution Klercide Premier - WFI 70/30 sterile IPA	LEVEL 3 106 min
75-12-7 Formamide 99%	LEVEL 3 99 min
110-54-3 n-Hexane 95%	LEVEL 3 97 min
Mixed Solution Klercide 70/30 sterile IPA	LEVEL 3 76 min
78-83-1 Isobutanol 99%	LEVEL 3 76 min

67-63-0 Isopropanol 70%	LEVEL 3 61 min
108-39-4 m-Cresol 98.5%	LEVEL 2 59 min
109-66-0 n-Pentane 98%	LEVEL 2 56 min
598-75-4 Secondary isoamyl alcohol 98%	LEVEL 2 55 min
108-87-2 Methylcyclohexane 99,9%	LEVEL 2 55 min
7697-37-2 Nitric Acid, 50%	LEVEL 2 49 min
110-82-7 Cyclohexane	LEVEL 6 480 min
79-06-1 Acrylamide 40%	LEVEL 6 480 min
67-63-0 Isopropanol 100%	LEVEL 2 43 min
67-68-5 Dimethyl Sulfoxide 99% (DMSO)	LEVEL 2 42 min
Mixed Solution Klercide Premier - WFI 60/40 sterile Alcohol	LEVEL 2 41 min
121-44-8 Triethylamine 99%	LEVEL 2 36 min
64-17-5 Ethanol 70%	LEVEL 2 31 min
108-95-2 Phenol 50%	LEVEL 1 24 min

64-17-5 Ethanol 99.8%	LEVEL 1 16 min
62-53-3 Aniline 99,9%	LEVEL 1 14 min
95-63-6 1,2,4- Trimethylbenzene 98%	LEVEL 1 13 min
97-88-1 Butyl methacrylate 99,9%	LEVEL 1 11 min
1634-04-4 Methyl Tert Butyl Esther (MTBE)	LEVEL 1 11 min
108-67-8 1,3,5-Trimethylbenzene 98%	LEVEL 1 10 min
7664-39-3 Hydrofluoric Acid 40%	LEVEL 1 10 min
127-19-5 Dimethyl Acetamide 99%	LEVEL 0 8 min
74-97-5 Bromochloromethane	LEVEL 3 66 min
64-19-7 Acetic Acid 100%	LEVEL 0 6 min
7664-39-3 Hydrogen Fluoride 48%	LEVEL 0 6 min
7664-93-9 Sulphuric acid 95%-98%	LEVEL 0 6 min
108-94-1 Cyclohexanone 99%	LEVEL 0 6 min
7664-39-3 Hydrofluoric Acid 48%	LEVEL 0 6 min

67-56-1 Methanol 99,9%	LEVEL 0 5 min
79-10-7 Acrylic acid 99%	LEVEL 0 4 min
68-12-2 Dimethyl Formamide 99%	LEVEL 0 4 min
71-36-3 Butanol 100%	LEVEL 2 39 min
37143-54-7 1-Methoxy-2-propylamine 95%	LEVEL 0 3 min
64-18-6 Formic acid 98,5%	LEVEL 0 3 min
1336-21-6 Ammonium Hydroxide 25%	LEVEL 1 28 min
1330-20-7 Xylene 98,5%	LEVEL 0 2 min
96-47-9 2-Methyltetrahydrofuran 99,9%	LEVEL 0 1 min
110-86-1 Pyridine	LEVEL 0 1 min
100-51-6 Benzyl Alcohol	LEVEL 0 9 min
75-56-9 Propylene oxide 99%	LEVEL 0 0 min
109-99-9 Tetrahydrofuran 99.9%	LEVEL 0 0 min
100-42-5 Styrene 99.9%	LEVEL 0 0 min

75-09-2
Dichloromethane 99%

LEVEL 0
0 min

107-21-1
Ethylene Glycol

LEVEL 0
0 min

67-66-3
Chloroform 99,8%

LEVEL 0
0 min

107-13-1
Acrylonitrile 99%

LEVEL 0
0 min

