

**Level 0**  
0 - <10 min

**Level 1**  
10 - 30 min

**Level 2**  
30 - 60 min


**Level 3**  
60 - 120 min

**Level 4**  
120 - 240 min

**Level 5**  
240 - 480 min

**Level 6**  
< 480 min

## SHIELDskin XTREME\* Sterile White Nitrile 330 DI+



- Category III PPE glove (PPE Directive 89/686/EEC)
- Complex Design - For mortal & irreversible risks
- Powder-free white nitrile glove
- Hand-specific
- 330 mm / 0.12 mm (EN 420:2003 + A1:2009)
- AQL 0.65 (EN 374-2:2014 Level 3)
- Viral penetration test (ISO 16604:2004 Procedure B & ASTM F1671-97b)
- Waterproof and for low chemical protection
- Tested for chemical permeation (EN 16523-1:2015 supersedes EN 374-3:2003)
- Typical particle levels: less than 900 per cm<sup>2</sup> more or equal 0.5µm
- Tested according to EN 1149-1-2-3 & 5
- Type I hypersensitivity eliminated - Type IV hypersensitivity reduced

108-95-2

Phenol aqueous solution 0.45%

**LEVEL 6**  
480 min  
DR -14  
%

Mixed Solution

Perform sterile PAA ready to use

**LEVEL 6**  
480 min

Mixed Solution

Perform sterile concentrate PAA 3%

**LEVEL 6**  
480 min

Mixed Solution

Perform sterile concentrate Oxy 2%

**LEVEL 6**  
480 min

7664-93-9

Sulphuric acid 50%

**LEVEL 6**  
480 min

7681-52-9

Sodium Hypochlorite 13%

**LEVEL 6**  
480 min

1310-73-2

Sodium Hydroxide 40%

**LEVEL 6**  
480 min

7722-84-1 Hydrogen Peroxide 30%	LEVEL 6 480 min
111-30-8 Glutaraldehyde 25%	LEVEL 6 480 min
50-00-0 Formaldehyde 37%	LEVEL 6 480 min
1239-45-8 Ethidium bromide 5%	LEVEL 6 480 min
67-63-0 Isopropanol 70%	LEVEL 4 155 min
Mixed Solution Klercide 70/30 sterile IPA	LEVEL 3 94 min
64-17-5 Ethanol 70%	LEVEL 3 76 min
142-82-5 n-Heptane 99%	LEVEL 2 56 min
Mixed Solution Klercide Premier - WFI 70/30 sterile IPA	LEVEL 2 55 min
79-06-1 Acrylamide 40%	LEVEL 6 480 min
67-63-0 Isopropanol 100%	LEVEL 2 44 min
Mixed Solution Klercide Premier - WFI 60/40 sterile Alcohol	LEVEL 1 23 min
64-17-5 Ethanol 99.8%	LEVEL 1 16 min
7664-93-9 Sulphuric acid 95%-98%	LEVEL 0 6 min

1330-20-7 Xylene 98,5%	<b>LEVEL 0</b> 3 min
1336-21-6 Ammonium Hydroxide 25%	<b>LEVEL 1</b> 27 min
67-64-1 Acetone 99,8%	<b>LEVEL 0</b> 1 min
80-62-6 Methyl Methacrylate 99%	<b>LEVEL 0</b> 1 min
75-09-2 Dichloromethane 99%	<b>LEVEL 0</b> 0 min
75-05-8 Acetonitrile 99,9%	<b>LEVEL 0</b> 1 min
109-89-7 Diethylamine 99,5%	<b>LEVEL 0</b> 0 min