




SHIELDskin XTREME* Eco Nitrile 300 DI+



- Category III PPE glove (PPE Regulation (EU) 2016/425)
- Complex Design - For mortal & irreversible risks
- Class 1 MDD glove (Council Directive 93/42/EEC)
- Powder-free white nitrile glove
- Ambidextrous
- 300 mm / 0.10 mm (EN 420:2003+A1:2009)
- Biological risk (ISO 374-5:2016 VIRUS)
- AQL 1.5 (EN 374-2:2014 Level 2)
- Viral penetration test (ISO 16604:2004 Procedure B)
- Chemical risk (ISO 374-1:2016+A1:2018 - Type B KPT)
- Waterproof and for low chemical protection
- Tested for chemical permeation (EN 16523-1:2015+A1:2018)
- Typical particle levels: less than 1100 per cm² more or equal 0.5µm

67-64-1 Acetone 99,8%	LEVEL 0 0 min
75-05-8 Acetonitrile 99,9%	LEVEL 0 0 min
79-06-1 Acrylamide 40%	LEVEL 6 480 min
1336-21-6 Ammonium hydroxide 25%	LEVEL 1 16 min
67-66-3 Chloroform 99,8%	LEVEL 0 0 min
109-89-7 Diethylamine 99,5%	LEVEL 0 0 min
68-12-2 Dimethyl formamide 99,8%	LEVEL 0 1 min

67-68-5 Dimethyl sulfoxide 99% (DMSO)	LEVEL 0 9 min
64-17-5 Ethanol 99,8%	LEVEL 1 11 min
64-17-5 Ethanol 70%	LEVEL 1 22 min
1239-45-8 Ethidium bromide 5%	LEVEL 6 480 min
141-78-6 Ethyl acetate 99.8%	LEVEL 0 0 min
50-00-0 Formaldehyde 37%	LEVEL 6 480 min
7647-01-0 Hydrochloric acid 37%	LEVEL 3 74 min
7647-01-0 Hydrochloric acid conc.	LEVEL 3 79 min
7664-39-3 Hydrofluoric acid 40%	LEVEL 0 8 min
7722-84-1 Hydrogen peroxide 30%	LEVEL 2 31 min
67-63-0 Isopropanol 100%	LEVEL 2 35 min
67-63-0 Isopropanol 70%	LEVEL 2 45 min
67-56-1 Methanol 99,9%	LEVEL 0 0 min
142-82-5 n-Heptane 99%	LEVEL 2 41 min

7697-37-2 Nitric acid 65%	LEVEL 0 5 min
108-95-2 Phenol 0.1% solution	LEVEL 6 480 min
1310-58-3 Potassium Hydroxide 40%	LEVEL 6 480 min
1310-73-2 Sodium Hydroxide 40%	LEVEL 6 480 min
1310-73-2 Sodium Hydroxide, 50%	LEVEL 6 480 min
7664-93-9 Sulphuric Acid 50%	LEVEL 6 480 min
75-59-2 Tetramethylammonium hydroxide 2.5%	LEVEL 6 480 min
1330-20-7 Xylene 98,5%	LEVEL 0 2 min

DISCLAIMER: The data provided was based on gloves tested under laboratory conditions, in accordance with EN 16523-1:2015 (formerly EN 374-3:2003) and EN 374-4:2013. The information is for guidance only and may not reflect the user's application. A risk assessment should always be made by purchaser to assess the suitability of gloves for a specific application.